

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-227119

(43)Date of publication of application : 02.09.1997

(51)Int.Cl.

C01B 33/44
B01J 13/00
C08L 61/28
C09D 5/02
C09D 7/12
C09D133/00
C09D167/08
C09D175/04
C09K 3/00

(21)Application number : 08-035093

(71)Applicant : NIPPON PAINT CO LTD

(22)Date of filing : 22.02.1996

(72)Inventor : OGAWA HIDEAKI


KUWAJIMA TERUAKI

(54) ORGANIC CLAY COMPLEX CONTAINING MELAMINE RESIN AND AQUEOUS COATING MATERIAL COMPOSITION CONTAINING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain an organic clay complex containing a melamine resin aiming at the improvement of the dispersibility in an aqueous medium and the improvement in waterproofness of the obtained coated membrane by using the same as a viscosity increasing agent for an aqueous coating material by introducing a quaternary ammonium ion and a melamine resin between the layers of swelling layered silicic acid salt.

SOLUTION: This organic clay complex containing a melamine resin is obtained by introducing (B) a quaternary ammonium ion commonly available as an organic bentonite and expressed by formula I [R1 to R4 are each H, a 1-24C alkyl or an aralkyl, one of R1 to R4 is a ≥6C alkyl) between the layers of (A) a swelling layered silicic acid compound such as a natural or a synthesized smectite-based clay mineral, a swelling mica, a vermiculite, etc., having ≥10meq per 100g exchanging capacity and containing ≤30wt.% non clay impurities, by



an ion exchange to obtain an organic clay complex material, then swelling the complex by contacting with an organic solvent and again introducing (C) a hydrophobic melamine resin soluble to an organic solvent, preferably having ≥ 1 triazine rings, and dissolved in the organic solvent.